



## Measurement of Uncertainty

### IDFL Europe AG:

Based upon 6 sets of internal round robin tests of the same material, the measurement of uncertainty is the following:

Composition Test:	1.8%
Species Test:	2.4%
Fill Power Test:	2.2% (or units = 4 mm / 30g)
Turbidity Test:	5.3% (or units = 0.12 NTU)
Oxygen Test:	0% (or units = 0 Oxygen Index Number) NOTE: All results in each set are identical.